

Caractéristiques techniques

| | | | | | | | | | | |
|---------------------|-----------|------|------|------|------|------|------|------|------|------|
| Inuit Ultra | g | 80 | 100 | 115 | 130 | 160 | 200 | 240 | 300 | 400 |
| Épaisseur | microns | 88 | 110 | 125 | 140 | 172 | 205 | 240 | 300 | 400 |
| Main | microns/g | 1.11 | 1.11 | 1.10 | 1.09 | 1.09 | 1.05 | 1.03 | 1.02 | 1.00 |
| Rugosité (Bendtsen) | ml/min | 70 | 70 | 70 | 70 | 70 | 70 | 70 | 70 | 70 |
| Opacité | % | 85 | 90 | 92 | 93 | 96 | n/a | n/a | n/a | n/a |
| Inuit Origin | g | 80 | 100 | 115 | 130 | 160 | 200 | 240 | 300 | 400 |
| Épaisseur | microns | 112 | 140 | 155 | 175 | 215 | 265 | 310 | 375 | 500 |
| Main | microns/g | 1.42 | 1.41 | 1.37 | 1.37 | 1.36 | 1.36 | 1.32 | 1.27 | 1.27 |
| Rugosité (Bendtsen) | ml/min | 400 | 400 | 400 | 400 | 400 | 400 | 400 | 400 | 400 |
| Opacité | % | 85 | 91 | 92 | 94 | 96 | n/a | n/a | n/a | n/a |

Inuit Deux finis (Ultra & Origin)

| | | | | | | | | | | |
|----------------------------|------------------------|--|--|--|--|--|--|--|--|-----|
| Blancheur – Blanc glacier | CIE/D65 (%) | | | | | | | | | 144 |
| Blancheur – Blanc blizzard | CIE/D65 (%) | | | | | | | | | 104 |
| Blancheur – Ivoire boréal | CIE/D65 (%) | | | | | | | | | 54 |
| Eclat – Blanc glacier | ISO2470 (%) | | | | | | | | | 92 |
| Eclat – Blanc blizzard | ISO2470 (%) | | | | | | | | | 85 |
| Eclat – Ivoire boréal | ISO2470 (%) | | | | | | | | | 77 |
| ISO9706 | Permanent (sans acide) | | | | | | | | | ✓ |